

Anisotropy of the gap parameter in the hole-doped cuprates

R. Szcześniak^{(1),*} A.P. Durajski⁽¹⁾, and D. Szcześniak⁽²⁾

1. *Institute of Physics, Częstochowa University of Technology,
Ave. Armii Krajowej 19, 42-200 Częstochowa, Poland and*

2. *Institute of Physics, Jan Długosz University in Częstochowa,
Ave. Armii Krajowej 13/15, 42-200 Częstochowa, Poland*

(Dated: April 16, 2013)

The structure of the gap parameter ($\Delta_{\mathbf{k}}$) for the hole-doped cuprates has been studied in the paper. In the first step, the equation for the anisotropic anomalous thermal average ($\phi_{\mathbf{k}}$) has been solved close to the Fermi energy. The obtained results indicate the $\phi_{\mathbf{k}}$ -amplitude crossover from the d -wave BCS to non-BCS behavior, as the electron-electron-phonon potential increases. In consequence, the antinodal part of the gap parameter is very weak temperature dependent and above the critical temperature (T_C), it extends into the anomalous normal state to the pseudogap temperature. On the other hand, the values of $\Delta_{\mathbf{k}}$, which are close to the nodal part, are temperature dependent and they disappear for $T > T_C$. The presented results strongly suggested that the pseudogap in the hole-doped cuprates is connected with the antinodal part of $2\Delta_{\mathbf{k}}$. The model has been tested for the $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ superconductor. It has been shown that the theoretical results agree with the experimental data.

The gap parameter ($\Delta_{\mathbf{k}}$) is strong anisotropic in the cuprates [1], [2]. In the case of the hole-doped superconductors, the d -wave symmetry is dominant [3], [4], [5]. In particular, for the optimally doped $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$, the experimental data suggests 83% d -wave anisotropy [6].

The issue of the wave symmetry for the electron-doped compounds is still unclear. Some experiments favor the s -wave symmetry [7], others support the d -wave anisotropy (penetration depth [8], [9], tricrystal [10], photoemission [11], [12], Raman scattering [13], and point contact tunneling [14]). Additionally, the point contact tunneling data [14] and the penetration depth experiment [15] suggest the energy gap crossover from the d - to s -wave symmetry, as the doping changes from the underdoped to overdoped region.

The gap parameter for the hole-doped cuprates can be most precisely measured by using the ARPES method [16]. So far, the obtained results have been interpreted in the framework of the two different approaches.

In the first case, the difference between the doping and temperature dependence of the gap in the nodal and antinodal region suggests that the pseudogap and the superconducting gap are independent [17], [18]. Additional support comes from the strong deviation from the standard d -wave form of the energy gap in the underdoped region. The above fact is interpreted as composing of the d -wave superconducting gap and the remnant pseudogap [19], [20].

In the second case, the pseudogap is considered as the precursor of the superconducting gap [21], [22]. The d -wave symmetry deviation in the underdoped region is connected with the existence of the high-harmonic pairing terms [23].

In the presented paper, we have studied the anisotropy of the gap parameter for the hole-doped superconductors in the framework of the recently introduced theory [24], [25], [26], [27]. In the above model, the pairing mechanism is based on the electron-phonon (EPH) and electron-electron-phonon (EPEP) interactions. It has been shown, that for strong EPEP coupling and $T < T_C$, the average gap parameter (Δ_{tot}) is very weak temperature dependent, and up to the critical temperature extends into the anomalous normal state: (i) in the s -wave case to the Nernst temperature, (ii) for the d -wave symmetry to the pseudogap temperature. We boldly underline that the discussed model explains well the experimental dependence of the ratio $R_1 \equiv 2\Delta_{tot}^{(0)}/k_B T_C$ on doping for the reported superconductors in the terms of the few fundamental parameters calculated by using the *ab initio* methods [24]. The symbol $\Delta_{tot}^{(0)}$ denotes the average gap parameter close to temperature of the zero Kelvin.

In the presented approach, the effective Hamiltonian for the high- T_C superconductors takes the form [24]:

$$H \equiv H^{(1)} + H^{(2)} + H^{(3)}. \quad (1)$$

The first term describes the non-interacting electrons:

$$H^{(1)} \equiv \sum_{\mathbf{k}\sigma} \varepsilon_{\mathbf{k}} c_{\mathbf{k}\sigma}^\dagger c_{\mathbf{k}\sigma}. \quad (2)$$

The band energy for the two-dimensional square lattice can be written as: $\varepsilon_{\mathbf{k}} = -t\gamma(\mathbf{k})$, where t denotes the nearest-neighbor hopping integral and $\gamma(\mathbf{k}) \equiv 2[\cos(k_x) + \cos(k_y)]$. The symbols $c_{\mathbf{k}\sigma}^\dagger$ and $c_{\mathbf{k}\sigma}$ are the creation and annihilation operators for the electron with momentum $\mathbf{k}$ and spin σ . The electron-phonon and

*Electronic address: szczesni@wip.pcz.pl

electron-electron-phonon effective terms are given by:

$$H^{(2)} \equiv - \sum_{\mathbf{k}_1 \mathbf{k}_2 \sigma} \frac{V_{\mathbf{k}_1 \mathbf{k}_2}}{2N_0} c_{\mathbf{k}_1 - \sigma}^\dagger c_{-\mathbf{k}_1 \sigma}^\dagger c_{-\mathbf{k}_2 \sigma} c_{\mathbf{k}_2 - \sigma}, \quad (3)$$

and

$$H^{(3)} \equiv - \sum_{\mathbf{k}_1 \sim \mathbf{k}_4 \sigma} \frac{U_{\mathbf{k}_1 \sim \mathbf{k}_4}}{2N_0^3} \phi_{\mathbf{k}_1 \sigma} \phi_{\mathbf{k}_2 \sigma}^* c_{-\mathbf{k}_3 \sigma} c_{\mathbf{k}_3 - \sigma} c_{\mathbf{k}_4 - \sigma}^\dagger c_{-\mathbf{k}_4 \sigma}^\dagger. \quad (4)$$

The parameter N_0 is the normalization factor: $N_0 \equiv 1/\sum_{\mathbf{k}}^{\omega_0}$; the symbol $\sum_{\mathbf{k}}^{\omega_0}$ denotes the sum over the states for which: $|\varepsilon_{\mathbf{k}}| \leq \omega_0$. The quantity ω_0 denotes the characteristic phonon frequency (ω_0 is of the order of Debye frequency). The functions $V_{\mathbf{k}_1 \mathbf{k}_2}$ and $U_{\mathbf{k}_1 \sim \mathbf{k}_4}$ represent the pairing potentials with the d -wave symmetry:

$$V_{\mathbf{k}_1 \mathbf{k}_2} \equiv V \eta(\mathbf{k}_1) \eta(\mathbf{k}_2), \quad (5)$$

and

$$U_{\mathbf{k}_1 \sim \mathbf{k}_4} \equiv U \eta(\mathbf{k}_1) \eta(\mathbf{k}_2) \eta(\mathbf{k}_3) \eta(\mathbf{k}_4), \quad (6)$$

where: $\eta(\mathbf{k}) \equiv 2[\cos(k_x) - \cos(k_y)]$. The anomalous thermal average is defined as: $\phi_{\mathbf{k}\sigma} \equiv \langle c_{-\mathbf{k}\sigma} c_{\mathbf{k}-\sigma} \rangle$.

The Green function for the superconducting state has been calculated using the operator (1) [28]. The result takes the form:

$$\langle \langle c_{\mathbf{k}\uparrow} | c_{-\mathbf{k}\downarrow} \rangle \rangle_{i\omega_n} = \frac{\frac{1}{N_0} \sum_{\mathbf{k}_2}^{\omega_0} W_{\mathbf{k} \mathbf{k}_2} \phi_{\mathbf{k}_2}}{\omega_n^2 + \varepsilon_{\mathbf{k}}^2 + M_{\mathbf{k}}^2}, \quad (7)$$

where $W_{\mathbf{k}_1 \mathbf{k}_2}$ can be written as: $W_{\mathbf{k}_1 \mathbf{k}_2} \equiv V_{\mathbf{k}_1 \mathbf{k}_2} + \frac{1}{N_0^2} \sum_{\mathbf{k}_3 \mathbf{k}_4}^{\omega_0} U_{\mathbf{k}_1 \sim \mathbf{k}_4} \phi_{\mathbf{k}_3} \phi_{\mathbf{k}_4}^*$, and $\phi_{\mathbf{k}} \equiv \phi_{\mathbf{k}\downarrow}$. The symbol: $\omega_n \equiv \frac{\pi}{\beta} (2n-1)$ denotes the n -th fermionic Matsubara frequency; $\beta \equiv 1/k_B T$, where k_B is the Boltzmann constant. The quantity $M_{\mathbf{k}}^2$ takes the form:

$$\begin{aligned} M_{\mathbf{k}}^2 &\equiv \left(\frac{1}{N_0} \sum_{\mathbf{k}_1}^{\omega_0} W_{\mathbf{k}_1 \mathbf{k}} \phi_{\mathbf{k}_1}^* \right) \left(\frac{1}{N_0} \sum_{\mathbf{k}_2}^{\omega_0} W_{\mathbf{k} \mathbf{k}_2} \phi_{\mathbf{k}_2} \right) \\ &= \eta^2(\mathbf{k}) \left(\frac{1}{N_0} \sum_{\mathbf{k}_1}^{\omega_0} \eta_{\mathbf{k}_1} \phi_{\mathbf{k}_1}^* \right) \left(\frac{1}{N_0} \sum_{\mathbf{k}_2}^{\omega_0} \eta_{\mathbf{k}_2} \phi_{\mathbf{k}_2} \right) \\ &\times \left[V + U \left(\frac{1}{N_0} \sum_{\mathbf{k}_3}^{\omega_0} \eta_{\mathbf{k}_3} \phi_{\mathbf{k}_3} \right) \left(\frac{1}{N_0} \sum_{\mathbf{k}_4}^{\omega_0} \eta_{\mathbf{k}_4} \phi_{\mathbf{k}_4}^* \right) \right]^2. \end{aligned} \quad (8)$$

On the basis of Eq. (7), we have derived the thermodynamic equation for the anomalous thermal average:

$$\begin{aligned} \phi_{\mathbf{k}} &= \left(\frac{1}{N_0} \sum_{\mathbf{k}_1}^{\omega_0} \eta(\mathbf{k}_1) \phi_{\mathbf{k}_1} \right) \\ &\times \left[V + U \left(\frac{1}{N_0} \sum_{\mathbf{k}_2}^{\omega_0} \eta(\mathbf{k}_2) \phi_{\mathbf{k}_2} \right) \left(\frac{1}{N_0} \sum_{\mathbf{k}_3}^{\omega_0} \eta(\mathbf{k}_3) \phi_{\mathbf{k}_3}^* \right) \right] \\ &\times \eta(\mathbf{k}) \chi_{\mathbf{k}}, \end{aligned} \quad (9)$$




FIG. 1: The amplitude of the anomalous thermal average close to the Fermi energy for selected values of the potential U . We have assumed: $V = 0.02t$ and $\omega_0 = 0.3t$.




FIG. 2: The phase of the anomalous thermal average close to the Fermi energy. We have assumed: $V = 0.02t$ and $\omega_0 = 0.3t$.

where:

$$\chi_{\mathbf{k}} \equiv \frac{\tan \left[\frac{i\beta}{2} \sqrt{\varepsilon_{\mathbf{k}}^2 + M_{\mathbf{k}}^2} \right]}{2i \sqrt{\varepsilon_{\mathbf{k}}^2 + M_{\mathbf{k}}^2}}. \quad (10)$$

We notice that Eq. (9) has been obtained with help of the relation: $\frac{1}{\beta} \sum_n \langle \langle B | A \rangle \rangle_{i\omega_n} = \langle AB \rangle$. In particular: $\frac{1}{\beta} \sum_n \frac{1}{\omega_n^2 + \varepsilon_{\mathbf{k}}^2 + M_{\mathbf{k}}^2} = \frac{1}{2i \sqrt{\varepsilon_{\mathbf{k}}^2 + M_{\mathbf{k}}^2}} \tan \left(\frac{i\beta}{2} \sqrt{\varepsilon_{\mathbf{k}}^2 + M_{\mathbf{k}}^2} \right)$.

The Eq. (9) has been solved for 7000 points close to the Fermi energy. The numerical result can be obtained




FIG. 3: The amplitude of the anomalous thermal average close to the Fermi energy for selected values of U and the temperature. In particular, the figure (A) is for $U = 0$, (B) for $U = 0.02t$, (C) for $U = 0.05t$, and (D) for $U = 0.1t$. We have assumed: $V = 0.02t$ and $\omega_0 = 0.3t$.

with help of the self-consistent iterative (SCI) procedure originally used for solving the Eliashberg equations defined on the imaginary axis [29], [30], [31], [32], [33], [34], [35], [36], [37]. We clearly underline that SCI procedure is very appropriate for the large sized system of the non-linear equations. The stability of the numerical solutions is ensured by replacing the initial values with the calculated values and repeatedly running the computer program. The computational errors can be controlled by solving the set independently of each in the framework of the Fortran and C programming language.

In Fig. 1, we have presented the amplitude of the anomalous thermal average ($|\phi_{\mathbf{k}}|$) close to the Fermi energy for different values of the potential U . The temperature takes the very low value ($k_B T = 10^{-4}t$). The obtained results show that beyond the nodal regions the low values of $|\phi_{\mathbf{k}}|$ strongly increase with the growth of U . For high values of U , the observed transition from the d -wave BCS to non-BCS behavior results in coming into existence the nearly-constant value of the amplitude in wide surroundings of the antinodal regions. In the nodal regions appear the characteristic "icicles" created by the wide range of $|\phi_{\mathbf{k}}|$ values.

In Fig. 2, we have plotted the phase of the anomalous thermal average ($\varphi_{\mathbf{k}}$). In contrast to the amplitude $|\phi_{\mathbf{k}}|$,

the phase is independent from the parameter U . Additionally, it has been shown that $\varphi_{\mathbf{k}}$ assumes two different values.

The temperature dependence of $|\phi_{\mathbf{k}}|$ for selected values of U has been presented in Fig. 3. In the first step, the case of $U = 0$ has been considered (Fig. 3 (A)). It is easy to see that the amplitude decreases with the grow of the temperature and disappearances at $T_C \simeq 0.0231t$. In other cases (Fig. 3 (B)-(D), where $U \neq 0$), the temperature dependence of $|\phi_{\mathbf{k}}|$ sharply differs from the prediction based on the pure d -wave model. In particular, for $0 < T < T_C$ the antinodal regions of $|\phi_{\mathbf{k}}|$ are very weak temperature dependent and above the critical temperature extend into the anomalous normal state to the pseudogap temperature. In contrast to the behavior of the antinodal values, the nodal regions of the amplitude strongly decrease with the grow of the temperature.

Now, we can calculate the gap parameter: $\Delta_{\mathbf{k}} \equiv \eta_{\mathbf{k}} |\phi_{\mathbf{k}}| [V + U |\eta_{\mathbf{k}}| |\phi_{\mathbf{k}}|^2]$. The form of the function $\Delta_{\mathbf{k}}$ has been presented in Fig. 4. In particular, we have selected the gap parameter for $U = 0$, close to the zero temperature ($k_B T = 10^{-4}t$), and the gap in the range of high value of the electron-electron-phonon potential ($U = 0.1t$) for two following temperatures: $k_B T = 10^{-4}t$ and $k_B T = 0.2339t$.




FIG. 4: The gap parameter close to the Fermi energy for selected values of U and the temperature. In particular, the figure (A) is for $U = 0$, (B) and (C) for $U = 0.1t$. We have assumed: $V = 0.02t$ and $\omega_0 = 0.3t$. The figures on the right show the general form of the gap; the blue surface represents the simple d -wave gap. The shape of the gap parameter in the nodal regions has been in detail presented in the figures on the left; the pink-blue surface represents the simple d -wave gap.

In the case of $U = 0$, one can easily see that the gap parameter very well reconstruct the shape of the simple d -wave gap ($\Delta_{\mathbf{k}}^{(\eta)} \equiv \Delta_{\eta}(\mathbf{k})$). However, the function $\Delta_{\mathbf{k}}$ possesses enough complicated internal structure. We notice also that in the nodal region the gap closely adjoins to the $\Delta_{\mathbf{k}}^{(\eta)}$ surface. Of course, the function $\Delta_{\mathbf{k}}$ decreases in the typical way with the increase of the temperature and assumes the zero value at $T_C \simeq 0.0231t$.

For the high value of the electron-electron-phonon potential and $k_B T = 10^{-4}t$, the amplitude of the gap strong increases and the internal structure of $\Delta_{\mathbf{k}}$ becomes much straighter (see Fig. 4 (B)). In the nodal region the gap agrees relatively well with the $\Delta_{\mathbf{k}}^{(\eta)}$ surface.

In the case of $U = 0.1t$ and $k_B T = 0.2339t$, one can observe anomalous behavior of the gap (Fig. 4 (C)). In the antinodal region $\Delta_{\mathbf{k}}$ has comparable values as for $k_B T = 10^{-4}t$. From the physical point of view the obtained result indicates that the pseudogap exists in the antinodal region. On the other hand, in the nodal region

the gap parameter forms the characteristic area of the very low values.

The model has been tested on the example of the $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ compound [38]. It has been assumed that the nearest-neighbor hopping integral and the characteristic phonon frequency take the values 250 meV and 75 meV, respectively [39], [40].

On the basis of the relations: $T_C = T_C(V)$ and $T^* = T^*(V, U)$, where T_C denotes the critical temperature and T^* is the pseudogap temperature, the pairing potentials have been uniquely determined. Then, the equation (9) has been solved, and the values of $2\Delta(\alpha)$ have been calculated, wherein $\alpha \equiv \arctan\left(\frac{k_y}{k_x}\right)$.

The theoretical and the experimental results have been compared with each other in Fig. 5. It can be easily seen that the presented model in the correct way predicts the course of the experimental data.

In the paper, we have tested the microscopic model for the high- T_C superconductivity, which is based on the electron-phonon and electron-electron-phonon interaction. In particular, the structure of the gap parameter has been studied. The presented results have been obtained using the thermodynamic equation for the anomalous thermal average.

It has been stated that for $U = 0$, the gap parameter very well reconstruct the d -wave behavior. However, $\Delta_{\mathbf{k}}$ possesses complicated internal structure.

In the opposite case (the large value of U) the behavior of the gap parameter is anomalous. In particular, the antinodal part of $\Delta_{\mathbf{k}}$ is very weak temperature dependent and above T_C it extends into the anomalous normal state to the pseudogap temperature. On the other hand, the nodal part is temperature dependent and for $T > T_C$ the values of the gap disappear. The above results suggested that the pseudogap in the hole-doped cuprates is connected with the antinodal part of the energy gap.

In the last paragraph, let us notice that the presented model has been tested for the $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ compound. Good agreement between the theoretical predictions and the experimental results has been achieved.

Acknowledgments

The authors would like to thank Prof. K. Dziliński and Prof. Z. Bąk for providing excellent working conditions and financial support.

Additionally, we are grateful to the Częstochowa University of Technology - MSK CzeŹMAN for granting access to the computing infrastructure built in the project No. POIG.02.03.00-00-028/08 "PLATON - Science Services Platform".




FIG. 5: The dependence of the energy gap (2Δ) on the angle for the $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ compound. The circles represent the theoretical results. The squares are the experimental data [38].

-
- [1] J. G. Bednorz and K. A. Müller, Z. Phys. B **64**, 189 (1986).
- [2] J. G. Bednorz and K. A. Müller, Rev. Mod. Phys. **60**, 585 (1988).
- [3] E. Dagotto, Rev. Mod. Phys. **66**, 763 (1994).
- [4] D. J. V. Harlingen, Rev. Mod. Phys. **67**, 515535 (1995).
- [5] C. C. Tsuei and J. R. Kirtley, Rev. Mod. Phys. **72**, 969 (2000).
- [6] H. J. H. Smilde, A. A. Golubov, Ariando, G. Rijnders, J. M. Dekkers, S. Harkema, D. H. A. Blank, H. Rogalla, and H. Hilgenkamp, Phys. Rev. Lett. **95**, 257001 (2005).
- [7] N. P. Armitage, P. Fournier, and R. L. Greene, Rev. Mod. Phys. **82**, 2421 (2010).
- [8] J. D. Kokales, P. Fournier, L. V. Mercaldo, V. V. Talanov, R. L. Greene, and S. M. Anlage, Phys. Rev. Lett. **85**, 3696 (2000).
- [9] R. Prozorov, R. W. Giannetta, P. Fournier, and R. L. Greene, Phys. Rev. Lett. **85**, 3700 (2000).
- [10] C. C. Tsuei and J. R. Kirtley, Phys. Rev. Lett. **85**, 182185 (2000).
- [11] N. P. Armitage, D. H. Lu, D. L. Feng, C. Kim, A. Damascelli, K. M. Shen, F. Ronning, Z.-X. Shen, Y. Onose, Y. Taguchi, et al., Phys. Rev. Lett. **86**, 1126 (2001).
- [12] T. Sato, T. Kamiyama, T. Takahashi, K. Kurahashi, and K. Yamada, Science **291**, 1517 (2001).
- [13] G. Blumberg, A. Koitzsch, A. Gozar, B. S. Dennis, C. A. Kendziora, P. Fournier, and R. L. Greene, Phys. Rev. Lett. **88**, 107002 (2002).
- [14] A. Biswas, P. Fournier, M. M. Qazilbash, V. N. Smolyanina, H. Balci, and R. L. Greene, Phys. Rev. Lett. **88**, 207004 (2002).
- [15] J. A. Skinta, M. S. Kim, T. R. Lemberger, T. Greibe, and M. Naito, Phys. Rev. Lett. **88**, 207005 (2002).
- [16] A. Damascelli, Z. Hussain, and Z. X. Shen, Rev. Mod. Phys. **75**, 473 (2003).
- [17] K. Tanaka, W. S. Lee, D. H. Lu, A. Fujimori, T. Fujii, Risdiana, I. Terasaki, D. J. Scalapino, T. P. Devereaux, Z. Hussain, et al., Science **314**, 1910 (2006).
- [18] W. S. Lee, I. M. Vishik, K. Tanaka, D. H. Lu, T. Sasagawa, N. Nagaosa, T. P. Devereaux, Z. Hussain, and Z. X. Shen, Nature (London) **450**, 81 (2007).
- [19] T. Kondo, T. Takeuchi, A. Kaminski, S. Tsuda, and S. Shin, Phys. Rev. Lett. **98**, 267004 (2007).
- [20] K. Terashima, H. Matsui, T. Sato, T. Takahashi, M. Kofu, and K. Hirota, Phys. Rev. Lett. **99**, 017003 (2007).
- [21] A. Kanigel, U. Chatterjee, M. Randeria, M. R. Norman, S. Souma, M. Shi, Z. Z. Li, H. Raffy, and J. C. Campuzano, Phys. Rev. Lett. **99**, 157001 (2007).
- [22] M. Shi, J. Chang, S. Pailhes, M. R. Norman, J. C. Campuzano, M. Mansson, T. Claesson, O. Tjernberg, A. Bendounan, L. Patthey, et al., Phys. Rev. Lett. **101**, 047002 (2008).
- [23] J. Mesot, M. R. Norman, H. Ding, M. Randeria, J. C. Campuzano, A. Paramekanti, H. M. Fretwell, A. Kaminski, T. Takeuchi, T. Yokoya, et al., Phys. Rev. Lett. **83**, 840843 (1999).
- [24] R. Szcześniak, PloS ONE **7** (4), art. no. e31873, 1 (2012).
- [25] R. Szcześniak, xxx.lanl.gov preprint: arXiv:1105.5525, 1 (2011).
- [26] R. Szcześniak, xxx.lanl.gov preprint: arXiv:1110.3404, 1 (2012).
- [27] R. Szcześniak and A. P. Durajski, xxx.lanl.gov preprint: arXiv:1206.5531, 1 (2012).
- [28] W. Gasser, E. Heiner, and K. Elk, Greensche Funktionen in Festkörper- und Vielteilchenphysik (VILEY-VCH Verlag GmbH, Weinheim, 1999).
- [29] R. Szcześniak and A. P. Durajski, Physica C **472**, 15 (2012).
- [30] R. Szcześniak and A. P. Durajski, J. Supercond. Nov. Magn. **25**, 399 (2012).
- [31] R. Szcześniak, A. P. Durajski, and M. W. Jarosik, Modern Physics Letters B **26**, 1250050 (2012).
- [32] R. Szcześniak and D. Szcześniak, Solid State Commun. **152**, 779 (2012).
- [33] R. Szcześniak and D. Szcześniak, Physica Status Solidi B **249**, 2194 (2012).
- [34] R. Szcześniak, D. Szcześniak, and E. Drzazga, Solid State Commun. **152**, 2023 (2012).
- [35] A. P. Durajski, R. Szcześniak, and M. W. Jarosik, Phase Transitions **85**, 727 (2012).

- [36] R. Szcześniak and M. W. Jarosik, *Acta Phys. Pol. A* **121**, 841 (2012).
- [37] R. Szcześniak and A. P. Durajski, *Solid State Commun.* **152**, 1018 (2012).
- [38] K. Nakayama, T. Sato, K. Terashima, T. Arakane, T. Takahashi, M. Kubota, K. Ono, T. Nishizaki, Y. Takahashi, and N. Kobayashi, *Phys. Rev. B* **79**, 140503(R) (2009).
- [39] T. S. Nunner, J. Schmalian, and K. H. Bennemann, *Phys. Rev. B* **59**, 8859 (1999).
- [40] K. P. Bohnen, R. Heid, and M. Krauss, *Europhys. Lett.* **64**, 104 (2003).